



# DYC20X

## EASY SPREAD SEMI-GLOSS INTERIOR WALL AND TRIM PAINT 200, 201, AND 202 Data Sheet

### CHARACTERISTICS

Dyco 200 is an excellent commercial grade semi-gloss interior vinyl acrylic latex enamel that is easy to apply, and has excellent touch up qualities. A very durable and washable finish makes it an ideal property maintenance paint.

### RECOMMENDED USES

- Interior Drywall/Gypsum Wall Board
- Interior Masonry Walls
- Interior Plaster
- Interior Brick
- Interior Wood
- Interior Primed Ferrous and Non-Ferrous Metals
- Interior Concrete Block (CMU)

### FEATURES/BENEFITS

- Durable Semi-Gloss Finish
- Excellent Washability
- Excellent Uniformity and Touch Up
- Mildew Resistant
- Easy to Apply and Fast Drying
- Easy Clean Up with Soap and Water

### RECOMMENDED PRIMERS

Interior Drywall/Gypsum..... 1055, 6005  
 Interior Masonry Walls ..... 1370, 1375, 6005  
 Interior Plaster or Brick ..... 1315, 1445, 6005  
 Interior Wood ..... 6005, 1410, 1445, 6020  
 Non-Ferrous Metals ..... MP-50, 1370, 1375, 6005  
 Ferrous Metals..... MP-50, MP-75, MP-90  
 Concrete Block Walls ..... 990

### FOR ADDITIONAL INFORMATION

See MSDS or call toll-free 1-800-282-7901.

### TECHNICAL DATA

Vehicle Type ..... Vinyl Acrylic Latex  
 Finish/Sheen ..... Semi-Gloss  
 Solids by Weight..... 45%  
 Solids by Volume..... 32%  
 Viscosity..... 103 ± 1 KU  
 VOC (less exempt solvents) ..... 70 g/L.  
 Weight per Gallon. .... 10.26 lbs.

### COVERAGE

250-300 S.F./Gal. @ 4.5 mils Wet; 1.4 mils DFT  
(Actual coverage may vary depending on type of substrate, and application method.)

### AVAILABLE BASES

- 200 White/Pastel
- 201 Tint Base
- 202 Deep Base

### KEY ATTRIBUTES

Application Temperatures: 50 - 110°F (10 - 43.33°C)  
 Application Tools: Brush, Roller, or Spray  
 Dry Times: Touch - 30 Minutes; Recoat - 1 Hour  
 (Dry Time Based on 77°F (25°C), 50% RH)  
 Thinner: If Necessary; ½ Pint Water per Gallon Max.  
 Clean Up: Warm Soapy Water

**NOTE:** Allow 30 Days Curing Before Washing

### PHYSICAL PROPERTIES

Perm Rating ..... N/A  
 Alkali Resistance..... N/A  
 Mildew Resistance ..... N/A  
 Flash Point..... 247°F (118.33°C)

### CERTIFICATIONS:

GS-11: VOC Compliant in all Regulated Areas



Sun Paints & Coatings • 4701 East 7th Ave • Tampa, FL 33605-4701  
 Phone: 1-800-247-9691 • Facsimile: 813-367-0263 • www.suncoatings.com

J-13  
R-1C



# DYC20X

## EASY SPREAD SEMI-GLOSS INTERIOR WALL AND TRIM PAINT 200, 201, AND 202 Precautions & Application Guide

**PRECAUTION:** Do not freeze. Wear protective clothing, gloves and eyewear during application and cleanup of this product. Do not transport on passenger seats or inside passenger compartment of any vehicle. Store product in cargo area of vehicle, and secure with protective cloths to prevent accidental spill damage. Do not store at temperature above 100°F (37.77°C). Do not use in drinking water or food systems.

**SURFACE PREPARATION (INTERIOR):** Previously Painted Surfaces: Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and let dry. Stains from water, smoke, nicotine, rust, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer. Mildew should be treated with fungicide, rinsed and dried before priming. Existing peeled or checked paint should be scraped and sanded to a sound surface and wiped clean. Glossy surfaces should be de-glossed by manual, mechanical or chemical methods and wiped clean. Caution: Use rubber gloves, work goggles and protective clothing during all cleaning procedures.

**DRYWALL:** Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust. Apply appropriate primer before painting.

**MASONRY, CONCRETE, CEMENT, AND CMU BLOCK:** All new surfaces must be cured according to the supplier's recommendations, usually about 30 days. Remove all form release and curing agents. Masonry surfaces must be dry before priming. Moisture content must be 15% or lower and the pH between 7 and 9. Rough surfaces should be filled by pointing or applying Dyco #990 Block Filler to provide a smooth surface. If painting cannot wait for a 30 day cure time, a manufacturer approved alkali blocking "Hot" masonry primer may be applied at a pH level between 7 and 12.

**FERROUS AND NON-FERROUS METALS:** Rust, oxidation and other surface contaminants must be removed from ferrous metals, aluminum, copper, brass and galvanized steel. Solvent wipe all metal surfaces thoroughly to remove residue with a solvent that is compatible with the adhesion of the primer to be used on the metal being painted. Apply appropriate primer before painting.

**WOOD:** All new wood should be sanded and wiped clean. Countersink all nails and putty holes flush with surface. Wood fillers, knots or resinous areas should be spot primed, then full primed with an appropriate stain blocking wood primer.

**APPLICATION INFORMATION:** Mixing: Read and follow label instructions before use. Tools: Apply with a brush, roller or airless sprayer. Brush: Use appropriate premium latex paint brushes for best results. Roller: Use a 1/4"- 3/8" nap cover for smooth surfaces, a 1/2" nap cover for semi-rough surfaces and a 3/4"-1"nap cover for rough surfaces. Airless sprayer: It is recommended to use a "minimum" 1 gallon per minute pump; with .015 -.019 tips, @ 1800-2400 psi;

and a 1/4" high pressure material hose. Adjust pressure as needed for desired results.

**COVERAGE:** Actual coverage may vary depending on substrate and application method. For best "hide", use appropriate grey basecoat or tint primers towards finish coat color. Certain deep or accent colors may require multiple coats to obtain even coverage and hide.

**THINNING:** The product is ready to use as is, but if thinning is deemed necessary, thin with clean water up to a maximum of 1/2 pint per gallon.

**LIMITATIONS:** If two coats are needed, allow the first coat to dry at least 1 hour before applying the second coat. Do not apply if surface is damp or not fully cured. Do not apply in direct sunlight or when air or surface temperature is below 50°F (10°C) or above 114°F (45.55°C). Do not apply if temperature is less than 5°F (2.7°C) above dew point.

### CAUTION!

**HARMFUL IF SWALLOWED. MAY CAUSE EYE, SKIN AND RESPIRATORY IRRITATION. USE WITH ADEQUATE VENTILATION. DO NOT TAKE INTERNALLY. KEEP CLOSED WHEN NOT IN USE. KEEP OUT OF REACH OF CHILDREN.**

**WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**CALIF. PROP. 65 • CHEMICAL WARNING:** This product contains chemicals known to the State of California to cause cancer, birth defects or other reproductive harm. Use proper protection and adequate ventilation, when using product.

**FIRST AID:** If you experience difficulty in breathing, leave area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

Material Safety Data Sheet available upon request.



Sun Paints & Coatings • 4701 East 7th Ave • Tampa, FL 33605-4701  
Phone: 1-800-247-9691 • Facsimile: 813-367-0263 • [www.suncoatings.com](http://www.suncoatings.com)

J-13  
R-1C